

JAMAIL HARDWOODS

SUPPLIER · INSTALL · DESIGN

DATA SHEET

Jamail Max

Wide-Plank European White Oak

Houston's B2B Hardwood Flooring Partner

2643 Colquitt St · Houston, TX 77098 · By Appointment

832-930-5936 · trade@jamailhardwoods.com · jamailhardwoods.com

RIVA\MAX

Pearl
Name

10"
Width

Character
Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Character solid knots up to 3" (70mm) permitted. Open knots with fill less than 2" (50mm). Repaired cracks or splits within the planks are permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Pearl **10"** **Select**
Name Width Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Select, solid knots up to 10 mm permitted in less 10% of the material. Open knots with fill, not permitted. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Cotton
Name

10"
Width

Character
Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Character solid knots up to 3" (70mm) permitted. Open knots with fill less than 2" (50mm). Repaired cracks or splits within the planks are permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Cotton
Name

10"
Width

Select
Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Select, solid knots up to 10 mm permitted in less 10% of the material. Open knots with fill, not permitted. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Mercury
Name

10"
Width

Character
Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Character solid knots up to 3" (70mm) permitted. Open knots with fill less than 2" (50mm). Repaired cracks or splits within the planks are permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Mercury
Name

10"
Width

Select
Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Select, solid knots up to 10 mm permitted in less 10% of the material. Open knots with fill, not permitted. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Smoke
Name

10"
Width

Character
Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Character solid knots up to 3" (70mm) permitted. Open knots with fill less than 2" (50mm). Repaired cracks or splits within the planks are permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Smoke
Name

10"
Width

Select
Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Select, solid knots up to 10 mm permitted in less 10% of the material. Open knots with fill, not permitted. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Sand **10"** **Character**
Name Width Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Character solid knots up to 3" (70mm) permitted. Open knots with fill less than 2" (50mm). Repaired cracks or splits within the planks are permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Sand **10"** **Select**
Name Width Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Select, solid knots up to 10 mm permitted in less 10% of the material. Open knots with fill, not permitted. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Earth
Name

10"
Width

Character
Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Character solid knots up to 3" (70mm) permitted. Open knots with fill less than 2" (50mm). Repaired cracks or splits within the planks are permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Earth Name 10" Width Select Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Select, solid knots up to 10 mm permitted in less 10% of the material. Open knots with fill, not permitted. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Crystal **10"** **Character**
Name Width Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal ± 0.1%
Width	Nominal ± 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Character solid knots up to 3" (70mm) permitted. Open knots with fill less than 2" (50mm). Repaired cracks or splits within the planks are permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement ≤ 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	ΔLw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Crystal **10"** **Select**
Name Width Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Select, solid knots up to 10 mm permitted in less 10% of the material. Open knots with fill, not permitted. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Krypton
Name

10"
Width

Character
Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Character solid knots up to 3" (70mm) permitted. Open knots with fill less than 2" (50mm). Repaired cracks or splits within the planks are permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Krypton **10"** **Select**
Name Width Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Select, solid knots up to 10 mm permitted in less 10% of the material. Open knots with fill, not permitted. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Amber
Name

10"
Width

Character
Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Character solid knots up to 3" (70mm) permitted. Open knots with fill less than 2" (50mm). Repaired cracks or splits within the planks are permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Amber **10"** **Select**
Name Width Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Select, solid knots up to 10 mm permitted in less 10% of the material. Open knots with fill, not permitted. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Cigar **10"** **Character**
Name Width Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Character solid knots up to 3" (70mm) permitted. Open knots with fill less than 2" (50mm). Repaired cracks or splits within the planks are permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com



RIVA\MAX

Cigar **10"** **Select**
Name Width Grade



DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Birch Phenolic Plywood and an Oak Plank Top Layer, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	5/8" (16mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	12 mm
Length (ft)	6-8'
Width (in)	10"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal \pm 0.1%
Width	Nominal \pm 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

GRADE

Select, solid knots up to 10 mm permitted in less 10% of the material. Open knots with fill, not permitted. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement \leq 0.29%
Formaldehyde Emission (EN-120)	E0. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	Δ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com

